



PU GLOSS # 507 CLEAR

General Description:

PU GLOSS # 507 CLEAR is a polyurethane glossy varnish based on poly – functional saturated polyester resin. A varnish of two component materials with excellent covering properties and optimum brilliant finish. Due to its high solid content, it provides a U.V. resistance; resistant to weathering and some limited acid spillage.

Major Uses:

Highly recommended for household furniture such as beds, cabinets, chairs, sofas, doors and frames turned pieces and likes.

Characteristics and Physical Properties:

Appearance	Liquid Transparent.
Specific Gravity (20 ⁰ C)	0.94 Kgs. / lit.
Viscosity (25 ⁰ C,FC # 4)	25 +/- 0.5 Sec.
Flash Point	21 ⁰ C
Non – Volatile (Wt.%)	Base : 48 +/- 0.5 Hardener : 41 +/- 0.5
Application Condition Air Temperature Relative Humidity	5 ~ 35 ⁰ C Max. 85%
Application Method	Brush, Spray or Roller
Recommended Catalyst	Catalyst # 003
Thinner	PU Thinner # 105
Mixing / Dilution Ratio (wt%)	Base : Hardener : Thinner 100 50 35 - 50
Pot Life (20 ⁰ C)	6 ~ 8 hrs.
Drying Time (20 ⁰ C) Dust Free To Touch To Recoat Hard	10 – 20-min. 35 – 45 min. 2 – 3 hrs. 24 – 36 hrs.
Coverage	5 ~ 7 m ² / lit. (90-120gms / m ²)
Recoating	minimum 30 min ~ max 3 hrs. medium sanding with 240 / 360 mesh sand paper is recommended before subsequent coat is needed.

The above information is given to the best of our knowledge based on laboratory test and practical experience. However, as the paint is often used under condition beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without prior notice.

Method of Application:

- The surface to be topcoated should be primed with either polyurethane primer or polyester primer.
- It should be cleaned, well – sanded and free from dust, oil, water and other contaminants.
- To a well – prepared surface, apply 1 – 2 coats of P.U. GLOSS # 507 CLEAR, horizontally and vertically.

Packing:

Available in 1Usg, 20 lit. Pail and 200lit Drum.

Storage:

Shelf life 12 months minimum if stored below 25⁰C.

Cleaning of Tools:

All tools should be cleaned with Wash Thinner or PU Thinner # 105.

Physiological Hazards:

PU GLOSS # 507 CLEAR and Catalyst # 003 do not contain dangerous solvents, nevertheless, good ventilation in working rooms is recommended as well as the use of safety tools and equipment. PU GLOSS # 507 CLEAR is flammable and harmful if swallowed. If contact with eyes or skin occurs, wash well with fresh water and seek immediate medical advise.

FACTORY : P.O. BOX NO: 23085,SAJJAH INDUSTRIAL AREA, SHARJAH, U.A.E
TEL : 06 – 5311777, FAX 06 - 5311330:
SHOWROOM : P.O. BOX NO: 23085,INDUSTRIAL AREA, SHARJAH, U.A.E
TEL : 06 – 5328533, FAX 06 - 5328610
Website : <http://www.maspaints.com/> Email : masuae@emirates.net.ae



D-111/2004