



CHLORO COAT PRIMER

General Description:

CHLORO COAT PRIMER is a chlorinated rubber based undercoat for anti – corrosion under extreme conditions.

Major Uses:

For steel, concrete and masonry surfaces in chemical plants, sewage plants, water treatment plants and metal processing plants.

Advantages:

- Inert to alkalis and excellent to moisture.
- Excellent flexibility.
- Resistance to chipping and cracking.
- Resistance to mold and fungus.
- Good resistance to weathering and chalking.
- Easy to apply.

Characteristics and Physical Properties:

Color	Red, White and Grey
Volume Solids	43%
Specific Gravity	1.31
Flash Point	24°C
Coverage	5 – 8 m ² / lit.
Dft.	75 microns.
Application	By Roller, Brush or Spray.

Application Details:

Method of application	By brush, roller, airless and Conventional spray.
Spray Data	
Conventional Spray	
Nozzle Orifice	2 – 3 mm.
Nozzle Pressure	43 – 57 psi.
Dilution	5 – 10%
Thinner	# 155
Airless	
Nozzle Orifice	0.38 - 0.46 mm.
Nozzle Pressure	1138 – 1710 psi.
Dilution	0 – 5%
Thinner	# 155

Application Conditions - Temperature of the substrate should be minimum 5°C.

The above information is given to the best of our knowledge based on laboratory test and practical experience. However, as the paint is often used under condition beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without prior notice.

FACTORY : P.O. BOX NO: 23085, SAJJAH INDUSTRIAL AREA, SHARJAH, U.A.E
 TEL : 06 – 5311777, FAX 06 - 5311330:

SHOWROOM : P.O. BOX NO: 23085, INDUSTRIAL AREA, SHARJAH, U.A.E
 TEL : 06 – 5328533, FAX 06 - 5328610

Website : <http://www.maspaints.com/> Email : masuae@emirates.net.ae



D-111/2004

Surface Preparation:

Steel substrate must be clean, dry and sandblasted to Sa 2 ½ . If sandblasting is not applicable, wire brushing is recommended for minor touch – up. Substrate must be free from, oil, grease and other contaminants.

Storage:

Store in cool areas below 25°C. Shelf life is 12 months in closed container. Keep container tightly close. Handle with care and stir well before using.

Cleaning of Tools:

All tools should be cleaned with Wash Thinner or Epoxy Thinner # 185 as soon as possible.

Packing:

Available in 1Usg.and 20 lit Pail.

Physiological Hazards:

CHLORO COAT PRIMER does not contain dangerous solvents, nevertheless, good ventilation n working rooms is recommended as well as the use of safety tools and equipment. CHLORO COAT PRIMER is flammable and harmful if swallowed. If contact with eyes or skin occurs, wash well with fresh water and seek immediate medical advise.