



# PRECATALYZED SEALER

## General Description:

PRECATALYZED SEALER is a mono component clear basecoat formulated to give deep grained timbers such as crown cut mahogany and other related woods, to overcome problems of aeration. It has good covering properties and sandability.

## Major Uses:

Recommended to open pored or semi open pored wood in a PU system, AC system or nitrocellulose system.

## Advantages:

- Easy application
- Fast drying
- Good adhesion resistance.
- Good abrasion
- Easy to handle and maintenance.

## Characteristics and Physical Properties:

Appearance	opalescent
Viscosity	45 “ # 4 FC
Specific Gravity	0.94
Solid Content	33 +/- 0.5
Flash Point	20 <sup>0</sup> C
Gloss	matt
Coverage	8 –10 sq.m/ltr
<b>Drying Time:</b>	
Dust Free	5 – 10 min.
Touch Dry	10 – 15 min.
Sandable	30 – 40 min.
Recoatable	1 - 2 hrs.

*The above information is given to the best of our knowledge based on laboratory test and practical experience. However, as the paint is often used under condition beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without prior notice.*

## Method of Application:

- Precatalyzed Lacquer is applied by using pneumatic or airless spray gun after diluting by 20 to 30% with NC Thinner # 115
- When applied by curtain coater. The product must be diluted to a viscosity of 20 secs. Ford cup # 4. to keep viscosity constant, periodically add thinner # 115 to the curtain coater bath.
- Apply at a maximum rate of 120 gm /m<sup>2</sup>. If temperature on working area and humidity is high, add 3 – 5% of Retarder Thinner to the product.

## Storage:

PRECATALYZED SEALER should be kept in cool area below 25<sup>0</sup>C. Keep tightly closed container

## Cleaning of Tools:

All tools should be cleaned with Wash Thinner or NC Thinner # 115 as soon as possible.

## Packing:

Available in 1Usg, 20 lit Pail, 200 lit Drum.

## Physiological Hazards:

PRECATALYZED SEALER does not contain dangerous solvents, nevertheless, good ventilation n working rooms is recommended as well as the use of safety tools and equipment. PRECATALYZED SEALER is flammable and harmful if swallowed. If contact with eyes or skin occurs, wash well with fresh water and seek immediate medical advise.

FACTORY : P.O. BOX NO: 23085,SAJAH INDUSTRIAL AREA, SHARJAH, U.A.E  
TEL : 06 – 5311777, FAX 06 - 5311330:  
SHOWROOM : P.O. BOX NO: 23085,INDUSTRIAL AREA, SHARJAH, U.A.E  
TEL : 06 – 5328533, FAX 06 - 5328610  
Website : <http://www.maspaints.com/> Email : masuae@emirates.net.ae



**D-111/2004**