



MASBERTO SMOOTH

General Description:

A high quality smooth and fine textured finish. Its drying time allows to create the required designs.

Major Uses:

For interior and exterior protection and decoration.

Advantages:

- Alkaline resistant.
- Water vapour permeable.
- Good colour retention properties.
- Good weather resistance.
- Scrub resistance.
- Good adhesion, abrasion.
- Various texture patterns
- Easy to apply.

Characteristics and Physical Properties:

Colour	White and as per requirement.
Gloss	Matt
Specific Gravity	1.72 +/- 0.4
Solid content	55-60% by volume
Coverage	5 – 6 m ² / lit. @100 microns Dft.
Touch Dry	3 hrs.
Dry to recoat	24 hrs.
Shelf Life	12 months
Flash Point	above 65 ⁰ C
Application	By brush or roller and airless spray gun.
Thinning / cleaning	Water.

Surface Preparation:

New Substrates:

- Substrate must be dry and free from any form of contaminants.
- Apply 1 – 2 coats of Mas Masonry Primer into the substrate. For gypsum and powdery surface apply 1 coat of MAS AR Primer.
- Apply MASBERTO SMOOTH as per the required design.

Old Concrete (previously painted)

- Remove all blistered, cracked and peeled off paint from the surface.
- Penetrated paint must be cleared and treated with 3% ammonia and water.
- Glossy finish coat must be sanded.
- Apply 1 coat of Masonry Primer White before application of MASBERTO SMOOTH.

Method of Application:

Instruction for use	
Spetter Coat	
Recommended Thinner	-Sweet Water.
Volume of Thinner	-approx.0 -5%
Nozzle Orifice	- 4. 0 mm.

Roller	
Recommended Thinner	-Sweet Water.
Volume of Thinner	-approx.0 -5%
For cleaning	-Sweet Water.

Storage:

The product must be stored in accordance with national regulations. The product should be kept in a cool and well ventilated place, protected from heat and direct sunlight. Contents must be kept tightly closed.

Cleaning of Tools:

All tools should be cleaned with water.

Packing:



Available in 1Usg. and 5 Usg. Pail

Precautions:



See Safety Indication Sheet.

The above information is given to the best of our knowledge based on laboratory test and practical experience. However, as the paint is often used under condition beyond our control, we cannot guarantee anything but the quality of the paint itself. We reserve the right to change the given data without prior notice.

FACTORY	:	P.O. BOX NO: 23085,SAJJAH INDUSTRIAL AREA, SHARJAH, U.A.E TEL : 06 – 5311777, FAX 06 - 5311330:	 
SHOWROOM	:	P.O. BOX NO: 23085,INDUSTRIAL AREA, SHARJAH, U.A.E TEL : 06 – 5328533, FAX 06 - 5328610	
Website	:	http://www.maspaints.com/ Email : masuae@emirates.net.ae	D-111/2004